



LIQUID VINYL SIDING™

EXTERIOR VINYL COATING

LV-196W6001

Features

- Natural Satin-like Appearance
- 10-15X Thicker Than Paint
- Bridges gaps Up To 1/8 inch
- Dry To The Touch in Under 1 Hour
- Mildew Resistant
- Durable & Long Lasting
- Superior Protection Against Weathering
- Low in Volatile Organic Compounds
- Environmentally Friendly
- Soap & Water Clean-up

Recommended For

Exterior surfaces Wood, Stucco, Brick, Concrete, Cement block, Composite siding, Hardi-Plank®, Galvanized metal, Aluminum siding, Vinyl siding, etc.

Recommended for exterior use on properly primed metal, masonry surfaces and stable trim substrates such as cedar.

General Description

Liquid Vinyl Siding™ is a premium quality waterborne vinyl coating for exterior applications. When used with Vinyl ProPrime™ base coat, Liquid Vinyl Siding™ provides unparalleled long-term performance. Liquid Vinyl forms a highly permeable membrane with excellent waterproofing ability. The vinyl coating can adhere to surfaces that may not hold paint. Liquid Vinyl Siding leaves a smooth-to-the-touch surface that looks natural and cleans easily.

Limitations

- Apply when air, surface and product temperature is above 50°F. Temperatures should remain above 50°F for 2 hours after coating and above 40°F for the first 48 hours after application.
- Moisture content of the substrate must be below 14%
- Not recommended for redwood or decking boards.
- Not intended for immersion service or continuous water contact. Not for below grade applications.

Product Information

COLORS - STANDARD:

White (LVSW)

- Tint Bases:

Liquid Vinyl Siding bases: White, Medium, Deep Neutral
Can be tinted using standard paint formulas. Tint strength tested for universal colorant.

APPLICATION:

Apply with Polyester Brush, Roller with medium nap cover or Airless Sprayer. Do not apply in direct sunlight or on a hot surface. Avoid rain and moisture for the first 48 hours of curing.

- Airless Sprayer:

For Liquid Vinyl Siding spray application, use recommended spray equipment. Contact Technical support at 1-888-409-2023 for current recommendations.

- Spray Tip Selection:

Airless tips in the range of 419 to 525 are ideally used to spray Liquid Vinyl Siding. 419 and 521 are recommended tip sizes to start with. Only experienced applicators should use larger tips

CERTIFICATION:

VOC compliant in all regulated areas. Liquid Vinyl Siding complies with California Air resource Board (CARB) regulations.

TECHNICAL DATA[⊕]

| | WHITE |
|--|-----------------------------|
| Vehicle Type | Vinyl Co-polymer |
| Pigment Type | Titanium Dioxide |
| Volume Solids | 68.2% |
| Coverage per Gallon at Recommended film Thickness | No more than 100 Sq. Ft. |
| Recommended Film Thickness | 20 Mils |
| | - Wet |
| Thickness | 13 - 14 Mils |
| | - Dry |
| Depending on surface texture and porosity. Be sure to estimate the right amount of coating for the job. This will ensure uniformity and minimal disposal of the paint. | |
| Dry Time @ 77°F (25°C) @ 50% R.H. | 30 - 60 Minutes |
| | - Tack Free |
| | 1 - 2 Hours |
| | - To Recoat |
| | 30 - 45 Days |
| | - Full Cure |
| High humidity and cool temperatures will result in longer dry, recoat and service times. | |
| Dries By | Coalescence |
| Viscosity | 105 - 115 KU |
| Flash point | 232°F (TT-141, Method 4293) |
| Gloss / Sheen | 8 - 10 O.N. Matte |
| Surface Temperature at Application | 50°F (10°C) |
| | - Min |
| | 92°F (33°C) |
| | - Max |
| Thin With | Do Not Thin |
| Clean Up Thinner | Warm, Soapy Water |
| Weight Per Gallon | 11.0 lbs. |
| Storage Temperature | 40°F (4°C) |
| | - Min |
| | 100°F (38°C) |
| | - Max |

Volatile Organic Compounds (VOC)

98 grams/liter 0.82 lbs./gal

[⊕]Reported values are for White LVS. Contact dealer for values of other bases.